

Technical Data Sheet

HYDROTHERM® MT

Serie 159958

PRODUCT DESCRIPTION

Fast drying water based anticorrosive paint based on modified silicone resins and heavy metal free corrosion inhibiting pigments. Good adhesion on steel and stainless steel.

INTENDED USES

Particularly suitable as a single coat for protection of steel and stainless steel structures exposed to high temperatures (up to 600°C) as stoves, heat exchangers or muffler. HYDROTHERM MT can be used in combination with zinc silicate coatings and zinc silicone coatings (up to 400°C).

TECHNICAL INFORMATION

Product type	Water based modified silicone coat			
Colours	Limited colours			
Solids (% +/- 2)	35 (by Volume)	47 (by Weight)	SOV/VOC (g/liter)	<80 Directive 2004/42/CE
Specific Gravity (g/liter +/- 100)	1210		SOV/VOC (g/liter) (calculated)	<80 Directive 2010/75/CE
Flash Point (°C +/- 2)	not flammable			
Appearance	matt, smooth			
Temperature Resistance (°C)	600 (dry)			

APPLICATION DATA

Application Range	Film thickness per coat in micron		Theoretical spreading rate		Consumption
	Dry	Wet	m²/l	m²/kg	g/m²
	(min - max)	20 - 40	58 - 115	17.5 - 8.8	14.5 - 7.2
Typical	30	86	11.7	9.6	104

Room Temperature	min 10°C	Max 40°C	Relative Humidity	min 5%	Max 70%
Mixing Ratio	- (by weight)		- (by volume)		
Pot life	N.A.				
Thinner/Cleaner	clear water (max. 10% by weight)				

Application methods Airless or conventional spray, brush or roller.

Guideline for airless spray

Pressure at nozzle	15 Mpa (150 kp/cm ² , 2100 psi)
Nozzle tip	0,46 - 0,58 mm (0,018 - 0,023")

Ti.Pi.Ci. s.a.s. di C.M. Pinto & C.

Via Val Lerone, 21 – 16011 Arenzano (GE) – Tel. 0109111368 r.a. – Fax 0109134188
P.IVA e C.F. 01346900994 - <http://www.tipici.net> – e-mail: tech@tipici.net

HYDROTHERM® MT

Series 159958

SURFACE PREPARATION

STEEL: must be undamaged, degreased and dry, a more thorough preparation (blast cleaning to Sa 3 - Sa 2,5) will improve the performance.

STAINLESS STEEL: must be undamaged, degreased and dry.

CONDITION DURING APPLICATION

the temperature of the substrate should be min. 10°C and min. 3°C above the dew point of the air. The temperature and relative humidity should be measured in the vicinity of the substrate.

DRYING TIMES

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with: good ventilation (outdoor exposure or free circulation of air), recommended film thickness, one coat on top of inert substrate.

Substrate temperature	Surface Dry ¹	Hard Dry ²	Cured ³	Dry to recoat ⁴	
				minimum ⁵	Maximum ⁶
10°C		1 h	48 h	2,5 h	-
20°C		30-45 min.	24 h	1,5 h	-
30°C		30 min.	24 h	1 h	-

- 1
- 2 Data resulted by tests and experience in pratical applications. A good ventilation can improve the drying time.
- 3 Data resulted by tests and experience in pratical applications.
- 4 As provided for recoating with the same generic type of paint.
- 5 In case of multi-coat application, drying times will be influenced by the number in sequence and by the total thickness of previous coat applied.
- 6 The surface should be dry and free from contaminants before applying the next coat.

Given data must be considered as guidelines only. Actual drying time can only be decided at site, depending on age of existing system, generic types, numbers of coates, thinning, temperature, ventilation, etc.

THIS PRODUCT IS INTENDED FOR PROFESSIONAL USE ONLY

The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Ti.Pi.Ci.'s technical documentation.

STORAGE AND PACKAGING
STORAGE

the product should be stored in accordance with national regulations. The best storage conditions are to keep the packages in a dry space provided with adequate ventilation.

SHELF LIFE 12 months at room temperature.
PACKAGING 20 kg

HEALTH AND SAFETY

For detailed information on the health and safety hazards and precautions for the use of this product, we refer to the Material Safety Data Sheet.

Disclaimer

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under contitions beyond our control, we can not guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Document n° 100038

Review No 14 - November 2020

THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED (Downloaded 09 May 2024 from www.tipici.net)