

Technical Data Sheet

HYDRO MICACEO MT

Serie 159681

PRODUCT DESCRIPTION

Fast drying waterborne anticorrosive enamel with micaceous iron oxide and heavy metal free corrosion inhibiting pigments.

INTENDED USES

Designed for applications such as single coat finish, gives a valuable antique-look similar to that of wrought iron. Excellent adhesion to carbon steel. Suitable for gates, railings, wrought iron, greenhouses, gazebos, lamp posts, industrial installations, bridges, tanks, pipelines, cranes, masts, excavators, etc..

The fast drying allows the application of several coats throughout the day. For new works and maintenance operations, it can be diluted only with water.

TECHNICAL INFORMATION

Product type	Water based alkyd finish			
Colours	Color chart			
Solids (% +/- 2)	63 (by Volume)	66 (by Weight)	SOV/VOC (g/liter)	<20 Directive 2004/42/CE
Specific Gravity (g/liter +/- 100)	1520		SOV/VOC (g/liter) (calculated)	<20 Directive 2010/75/CE
Flash Point (°C +/- 2)	>65			
Appearance	matt, rough			
Temperature Resistance (°C)	90 (dry) - 110 (peak)			

APPLICATION DATA

Application Range	Film thickness per coat in micron		Theoretical spreading rate		Consumption
	Dry	Wet	m ² /l	m ² /kg	g/m ²
(min - max)	30 - 50	48 - 80	21 - 12.6	13.8 - 8.3	-
Typical	40	64	15.8	10.4	97

Room Temperature	min 10°C	Max 40°C	Relative Humidity	min 5%	Max 70%
Mixing Ratio	N.A. (by weight)		N.A. (by volume)		
Pot life	N.A.				
Thinner/Cleaner	clear water (max. 2% by weight)				

Application methods Airless, conventional spray, brush or roller.
NOTE: stir well the product before use.

Guideline for airless spray

Pressure at nozzle	15 Mpa (150 kp/cm ² , 2100 psi)
Nozzle tip	0,46 - 0,58 mm (0,018 - 0,023")

Ti.Pi.Ci. s.a.s. di C.M. Pinto & C.

Via Val Lerone, 21 – 16011 Arenzano (GE) – Tel. 0109111368 r.a. – Fax 0109134188
P.IVA e C.F. 01346900994 - <http://www.tipici.net> – e-mail: tech@tipici.net

HYDRO MICACEO MT

Series 159681

SURFACE PREPARATION

the substrate must be clean and dry. Surface contamination is to be removed by detergents and fresh water cleaning.

CONDITION DURING APPLICATION

the temperature of the substrate should be min. 10°C and min. 3°C above the dew point of the air. The temperature and relative humidity should be measured in the vicinity of the substrate.

DRYING TIMES

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with: good ventilation (outdoor exposure or free circulation of air), recommended film thickness, one coat on top of inert substrate.

Substrate temperature	Surface Dry ¹	Hard Dry ²	Cured ³	Dry to recoat ⁴	
				minimum ⁵	Maximum ⁶
10°C		1h - 1,5h	96h	8h	-
20°C		45min - 60min	48h	4h	-
30°C		30min - 45min	24h	2h	-

- 1
- 2 Data resulted by tests and experience in pratical applications. A good ventilation can improve the drying time.
- 3 Data resulted by tests and experience in pratical applications.
- 4 Recommended data given for recoating with same generic type of paint.
- 5 In case of multi-coat application, drying times will be influenced by the number in sequence and by the total thickness of previous coat applied.
- 6 The surface should be dry and free from any contamination prior to application of the subsequent coat.

Given data must be considered as guidelines only. Actual drying time can only be decided at site, depending on age of existing system, generic types, numbers of coates, thinning, temperature, ventilation, etc.

THIS PRODUCT IS INTENDED FOR PROFESSIONAL USE ONLY

The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Ti.Pi.Ci.'s technical documentation.

STORAGE AND PACKAGING

STORAGE the product should be stored in accordance with national regulations. The best storage conditions are to keep the packages in a dry space provided with adequate ventilation.

SHELF LIFE 12 months at room temperature.

PACKAGING 20 kg

HEALTH AND SAFETY

For detailed information on the health and safety hazards and precautions for the use of this product, we refer to the Material Safety Data Sheet.

Disclaimer

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under contitions beyond our control, we can not guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Document n° 100108

Review No 8 - April 2019

THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED (Downloaded 08 May 2024 from www.tipici.net)