

Technical Data Sheet

HYDROTHANE® Antigraffiti

Serie 160386

PRODUCT DESCRIPTION

Water based two pack fluorinated polyurethane topcoat with permanent anti-graffiti properties.

INTENDED USES

Formulated as a topcoat layer for water-based paint systems with anti-graffiti properties.

Extremely resistant to chemical attack, the film resists to many cycles of dirtying from spray and markers with subsequent cleaning using acetone.

HYDROTHANE Antigraffiti has been tested according to standard UNI 11246. This product contributes to the Green Buildings standard credits for LEED certification.

TECHNICAL INFORMATIONS

| | | | | |
|------------------------------------|--|--------------------------------|------|----------------------|
| Product type | Water based fluorinated polyurethane topcoat | | | |
| Colours | Ral colours | | | |
| Solids (% +/- 2) | 41 (by Volume) 46 (by Weight) | SOV/VOC (g/liter) | <135 | Directive 2004/42/CE |
| Specific Gravity (g/liter +/- 100) | 1110 | SOV/VOC (g/liter) (calculated) | <135 | Directive 2010/75/CE |
| Flash Point (°C +/- 2) | >55 | | | |
| Appearance | glossy | | | |
| Temperature Resistance (°C) | 90 (dry) - 110 (peak) | | | |

APPLICATION DATA

| Application Range | Film thickness per coat in micron | | Theoretical spreading rate | | Consumption |
|-------------------|-----------------------------------|-----------|----------------------------|--------------------|------------------|
| | Dry | Wet | m ² /l | m ² /kg | g/m ² |
| (min - max) | 30 - 50 | 74 - 122 | 13.7 - 8.2 | 12.3 - 7.4 | - |
| Typical | 40 | 98 | 10.3 | 9.2 | 109 |

| | | | | | |
|------------------|----------------------------------|----------|-------------------|--------|---------|
| Room Temperature | min 10°C | Max 40°C | Relative Humidity | min 5% | Max 80% |
| Mixing Ratio | 4 - 1 (by weight) | | 4 - 1 (by volume) | | |
| Pot life | 3 h | | | | |
| Thinner/Cleaner | clear water (max. 15% by weight) | | | | |

Application methods

Airless or conventional spray.

NOTE: mixing the two components separately, then catalyze the base and mixing the two components to obtain a homogeneous product. Mixing the two components viscosity of the product will increase. Then slowly add the water and under mixing dilution up to a maximum of 15% by weight.

Guideline for airless spray

| | |
|--------------------|--|
| Pressure at nozzle | 15 Mpa (150 kp/cm ² , 2100 psi) |
| Nozzle tip | 0,46 - 0,58 mm (0,018 - 0,023") |

Ti.Pi.Ci. s.a.s. di C.M. Pinto & C.

Via Val Lerone, 21 – 16011 Arenzano (GE) – Tel. 0109111368 r.a. – Fax 0109134188
P.IVA e C.F. 01346900994 - <http://www.tipici.net> – e-mail: tech@tipici.net

HYDROTHANE® Antigraffiti**Series 160386****SURFACE PREPARATION**

the substrate must be clean and dry. Surface contamination is to be removed by detergents and fresh water cleaning.

CONDITION DURING APPLICATION

the temperature of the substrate should be min. 10°C and min. 3°C above the dew point of the air. The temperature and relative humidity should be measured in the vicinity of the substrate.

DRYING TIMES

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with: good ventilation (outdoor exposure or free circulation of air), recommended film thickness, one coat on top of inert substrate.

| Substrate temperature | Surface Dry ¹ | Hard Dry ² | Cured ³ | Dry to recoat ⁴ | |
|-----------------------|--------------------------|-----------------------|--------------------|----------------------------|----------------------|
| | | | | minimum ⁵ | Maximum ⁶ |
| 10°C | | 4 - 5 h | 48 h | 12 h | - |
| 20°C | | 4 h | 36-48 h | 8 h | - |
| 30°C | | 2 - 3 h | 24-36 h | 6 h | - |

- 1
- 2 Data resulted by tests and experience in practical applications. A good ventilation can improve the drying time.
- 3 Data resulted by tests and experience in practical applications.
- 4 Recommended data given for recoating with same generic type of paint.
- 5 In case of multi-coat application, drying times will be influenced by the number in sequence and by the total thickness of previous coat applied.
- 6 The surface should be dry and free from any contamination prior to application of the subsequent coat.

Given data must be considered as guidelines only. Actual drying time can only be decided at site, depending on age of existing system, generic types, numbers of coats, thinning, temperature, ventilation, etc.

THIS PRODUCT IS INTENDED FOR PROFESSIONAL USE ONLY

The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Ti.Pi.Ci.'s technical documentation.

STORAGE AND PACKAGING

STORAGE the product should be stored in accordance with national regulations. The best storage conditions are to keep the packages in a dry space provided with adequate ventilation.

SHELF LIFE 6 mesi (teme il gelo)

PACKAGING 16 kg comp. A and 4 kg comp. B (20 kg KIT A+B)

HEALTH AND SAFETY

For detailed information on the health and safety hazards and precautions for the use of this product, we refer to the Material Safety Data Sheet.

Disclaimer

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we can not guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Document n° 100156

Review No 6 - August 2021

THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED (Downloaded 08 May 2024 from www.tipici.net)