

Technical Data Sheet

HYDROSINTEX®

Serie 159645 (mc 160394)

PRODUCT DESCRIPTION

One component water based alkyd finish.

INTENDED USES

Excellent coverage of the substrate, fast drying, high gloss, good protective properties in urban and industrial atmosphere. Particularly suitable as a finish coat of alkyd water based paint system or as a single coat on carbon steel and aluminum. HYDROSINTEX can also be used as a topcoat in classes C2, C3, and C4 (according to standard ISO 12944) on various primers. This product contributes to the Green Buildings standard credits for LEED certification.

TECHNICAL INFORMATION

Product type	Water based alkyd finish			
Colours	Ral colours			
Solids (% +/- 2)	34 (by Volume)	45 (by Weight)	SOV/VOC (g/liter)	<15 Directive 2004/42/CE
Specific Gravity (g/liter +/- 100)	1200		SOV/VOC (g/liter) (calculated)	<15 Directive 2010/75/CE
Flash Point (°C +/- 2)	not flammable			
Appearance	glossy			
Temperature Resistance (°C)	80 (dry) - 120 (peak)			

APPLICATION DATA

Application Range	Film thickness per coat in micron		Theoretical spreading rate		Consumption
	Dry	Wet	m ² /l	m ² /kg	g/m ²
(min - max)	30 - 50	89 - 148	11.3 - 6.8	9.4 - 5.7	-
Typical	40	118	8.5	7.1	142

Room Temperature	min 10°C	Max 40°C	Relative Humidity	min 5%	Max 70%
Mixing Ratio	N.A. (by weight)		N.A. (by volume)		
Pot life	N.A.				
Thinner/Cleaner	clear water (ready to use don't add water)				

Application methods Airless or conventional spray, brush or roller.

Guideline for airless spray

Pressure at nozzle	15 Mpa (150 kp/cm ² , 2100 psi)
Nozzle tip	0,46 - 0,58 mm (0,018 - 0,023")

Ti.Pi.Ci. s.a.s. di C.M. Pinto & C.

Via Val Lerone, 21 – 16011 Arenzano (GE) – Tel. 0109111368 r.a. – Fax 0109134188
P.IVA e C.F. 01346900994 - <http://www.tipici.net> – e-mail: tech@tipici.net

HYDROSINTEX®

Series 159645

SURFACE PREPARATION

the substrate must be clean and dry. Surface contamination is to be removed by detergents and fresh water cleaning.

CONDITION DURING APPLICATION

the temperature of the substrate should be min. 10°C and min. 3°C above the dew point of the air. The temperature and relative humidity should be measured in the vicinity of the substrate.

DRYING TIMES

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with: good ventilation (outdoor exposure or free circulation of air), recommended film thickness, one coat on top of inert substrate.

Substrate temperature	Surface Dry ¹	Hard Dry ²	Cured ³	Dry to recoat ⁴	
				minimum ⁵	Maximum ⁶
10°C		1 - 2 h	96 h	4 h	-
20°C		45 min - 1 h	48 h	2,5 h	-
30°C		30 - 45 min.	24 h	2 h	-

- 1
- 2 Data resulted by tests and experience in pratical applications. A good ventilation can improve the drying time.
- 3 Data resulted by tests and experience in pratical applications.
- 4 Recommended data given for recoating with same generic type of paint.
- 5 In case of multi-coat application, drying times will be influenced by the number in sequence and by the total thickness of previous coat applied.
- 6 The surface should be dry and free from any contamination prior to application of the subsequent coat.

Given data must be considered as guidelines only. Actual drying time can only be decided at site, depending on age of existing system, generic types, numbers of coates, thinning, temperature, ventilation, etc.

THIS PRODUCT IS INTENDED FOR PROFESSIONAL USE ONLY

The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Ti.Pi.Ci.'s technical documentation.

STORAGE AND PACKAGING
STORAGE

the product should be stored in accordance with national regulations. The best storage conditions are to keep the packages in a dry space provided with adequate ventilation.

SHELF LIFE 12 months at room temperature.
PACKAGING 20 kg

HEALTH AND SAFETY

For detailed information on the health and safety hazards and precautions for the use of this product, we refer to the Material Safety Data Sheet.

Disclaimer

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under contitions beyond our control, we can not guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.