

ID Protective system:

TIPICI-MT-0118-eng

Validation date

Downloaded

16/09/2015

05 May 2024 from
www.tipici.net

Generic description of structures:

Industrial areas with high humidity and aggressive atmosphere and coastal areas with high salinity.
Buildings or areas with almost permanent condensation and high pollution.

Surface type:

carbon steel

Category and Durability (ISO 12944-2 and 12944-1): C5-M
Accelerated aging (ASTM B117) - (hours): >2000
Max operative temperature (°C): <=120

Main system

Surface preparation		sandblasting	Standard	ISO 8501-1 2007 SSPC VIS-1	Preparation degree	Sa 2,5 SP10	Profile (micron)	50-85	
Type	Coat N°	Product definition					Dry Film Thickness (micron)		
							Min.	Specified	Max.
EP (WB)	1	HYDROGUARD SZ HYDROGUARD HB AL HYDROTHANE FL					50	80	100
EP (WB)	2						60	180	300
PUR (WB)	3						30	40	50
D.F.T. - Total Dry Film Thickness (micron)								300	

Repair of the main system

Surface preparation		brushing	Standard	ISO 8501-1 2007	Preparation degree	St3	Profile (micron)	N.A.	
Type	Coat N°	Product definition					Dry Film Thickness (micron)		
							Min.	Specified	Max.
EP (WB)	1	HYDROGUARD HB AL					60	160	300
PUR (WB)	2	HYDROTHANE FL					30	40	50
D.F.T. - Total Dry Fil Thickness (micron)							200		