

Surface preparation		brushing	Standard	ISO 8501-1 2007	Preparation degree	St3	Profile (micron)	N.A.
Type	Coat N°	Product definition				Dry Film Thickness (micron)		
						Min.	Specified	Max.
EP (WB)	1	HYDROGUARD HB MIO				60	150	250
PUR (WB)	2	HYDROTHANE				40	50	60
D.F.T. - Total Dry Fil Thickness (micron)							200	