

ID Protective system:

**TIPICI-MT-0138-eng**

Validation date

Downloaded

21/01/2014

05 May 2024 from  
www.tipici.net

Generic description of structures:

Buried tanks, steel piles, steel pipes

Surface type:

Carbon steel

Category and Durability (ISO 12944-2 and 12944-1):

Im3-H

Accelerated aging (ASTM B117) - (hours):

>3000 h per ISO 2812-2 >1440 per ISO 7253

Max operative temperature (°C):

<40

#### Main system

Surface preparation		Sandblasting	Standard	ISO 8501-1 2007 SSPC VIS1	Preparation degree	Sa 3 SP5	Profile (micron)	100-120	
Type	Coat N°	Product definition					Dry Film Thickness (micron)		
							Min.	Specified	Max.
EP (SL)	1	EPOXYMASTIC IB					200	300	500
EP (SL)	2	EPOXYMASTIC IB GF					200	300	500
D.F.T. - Total Dry Film Thickness (micron)								600	

#### Repair of the main system

Surface preparation			Standard		Preparation degree		Profile (micron)		
Type	Coat N°	Product definition					Dry Film Thickness (micron)		
							Min.	Specified	Max.
D.F.T. - Total Dry Fil Thickness (micron)								0	